



MEGA MEX, LP

1823 Rough Neck Dr.
Humble, TX 77338
Tel: 281-548-1544 Fax: 281-548-2477

VISITA NUESTRA PAGINA DE INTERNET
WWW.MEGAMEX.COM

Dims. En Pulgadas	D.E. En Pulgadas	Dimensiones y Pesos de los Tubos															
		5S	5	10S	10	20	30	40S & STD	40	60	80S & STD	80	100	120	140	160	DBLE. XXH
1/8	0.405		.035 .1383	.049 .1863	.049 .1863			.068 .2447	.068 .2447		.095 .3145	.095 .3145	NEGRO ESPESOR DE PARED EN PULGADAS				
1/4	0.540		.049 .2570	.065 .3297	.065 .3297			.088 .4248	.088 .4248		.119 .5351	.119 .5351	ROJO PESO POR PIE EN LIBRAS				
3/8	0.675		.049 .3276	.065 .4235	.065 .4235			.091 .5676	.091 .5676		.126 .7338	.126 .7338					
1/2	0.840	.065 .5383	.065 .5383	.083 .6710	.083 .6710			.109 .8510	.109 .8510		.147 1.088	.147 1.088				.187 1.304	.294 1.714
3/4	1.050	.065 .6838	.065 .6838	.083 .8572	.083 .8572			.113 1.131	.113 1.131		.154 1.474	.154 1.474				.218 1.937	.308 2.441
1	1.315	.065 .8678	.065 .8678	.109 1.404	.109 1.404			.133 1.679	.133 1.679		.179 2.172	.179 2.172				.250 2.844	.358 3.659
1 1/4	1.660	.065 1.107	.065 1.107	.109 1.806	.109 1.806			.140 2.273	.140 2.273		.191 2.997	.191 2.997				.250 3.765	.382 5.214
1 1/2	1.900	.065 1.274	.065 1.274	.109 2.085	.109 2.085			.145 2.718	.145 2.718		.200 3.631	.200 3.631				.281 4.859	.400 6.408
2	2.375	.065 1.604	.065 1.604	.109 2.638	.109 2.638			.154 3.653	.154 3.653		.218 5.022	.218 5.022				.344 7.462	.436 9.029
2 1/2	2.875	.083 2.475	.083 2.475	.120 3.531	.120 3.531			.203 5.793	.203 5.793		.276 7.661	.276 7.661				.375 10.01	.552 13.70
3	3.500	.083 3.029	.083 3.029	.120 4.332	.120 4.332			0.216 7.576	.216 7.576		.300 10.25	.300 10.25				.438 14.32	.600 18.58
3 1/2	4.000	.083 3.472	.083 3.472	.120 4.937	.120 4.937			.226 9.109	.226 9.109		.318 12.51	.318 12.51					.636 22.85
4	4.500	.083 3.915	.083 3.915	.120 5.613	.120 5.613			.237 10.79	.237 10.79	.281 12.66	.337 14.98	.337 14.98		.438 19.00		.531 22.51	.674 27.54
4 1/2	5.000							.247 12.53			.355 17.61						.710 32.53
5	5.563	.109 6.349	.109 6.349	.134 7.770	.134 7.770			.258 14.62	.258 14.62		.375 20.78	.375 20.78		.500 27.04		.625 32.96	.750 38.55
6	6.625	.109 7.585	.109 7.585	.134 9.289	.134 9.289			.280 18.97	.280 18.97		.432 28.57	.432 28.57		.562 36.39		.719 43.35	.864 53.16
7	7.625							.301 23.57			.500 38.05						.875 63.08
8	8.625	.109 9.914	.109 9.914	.148 13.40	.148 13.40	.250 22.36	.277 24.70	.322 28.55	.322 28.55	.406 35.64	.500 43.39	.500 43.39	.594 50.95	.719 60.71	.812 67.76	.906 74.79	.875 72.42
9	9.625							.342 33.90			.500 48.72						
10	10.750	.134 15.19	.134 15.19	.165 18.65	.165 18.65	.250 28.04	.307 34.24	.365 40.48	.365 40.48	.500 54.74	.500 54.74	.594 64.43	.719 77.03	.844 89.29	1.000 104.1	1.125 115.60	1.000 104.1
11	11.750							.375 45.55			.500 60.07						
12	12.750	.156 21.07	.165 22.18	.180 24.17	.180 24.17	.250 33.38	.330 43.77	.375 49.56	.406 53.52	.562 73.15	.500 65.42	.688 88.63	.844 107.30	1.000 125.50	1.125 139.70	1.312 160.30	1.000 125.50
14	14.000	.156 23.07		.188 27.73	.250 36.71	.312 45.61	0.375 54.57	.375 54.57	.438 63.44	.594 85.05	.500 72.09	.720 106.10	.938 130.90	1.094 150.80	1.250 170.20	1.406 189.10	
16	16.000	.165 27.90		.188 31.75	.250 42.05	.312 52.27	.375 62.58	.375 62.58	.500 82.77	.656 107.50	.500 82.77	.843 136.60	1.031 164.80	1.218 192.40	1.427 223.60	1.593 245.30	
18	18.000	.165 31.43		.188 35.76	.250 47.39	.312 58.94	.437 82.15	.375 70.59	.562 104.7	.750 138.20	.500 93.45	.937 170.90	1.156 208.00	1.375 244.10	1.562 274.20	1.781 308.50	
20	20.000	.188 39.78		.218 46.05	.250 52.73	.375 78.60	.500 104.1	.375 78.60	.594 123.1	.812 166.4	.500 104.1	1.031 208.9	1.280 256.1	1.500 296.4	1.750 341.1	1.969 379.2	
22	22.000	.188 43.80		.218 50.71	.250 58.07	.375 86.61	.500 114.81	.375 86.61	.875 197.41	.500 114.81	1.125 250.81	1.375 302.88	1.625 353.61	1.875 403.0	2.125 451.06		
24	24.000	.218 55.37		.250 63.41	.250 63.41	.375 94.62	.562 140.8	.375 94.62	.687 171.3	.968 238.4	.500 125.5	1.218 296.6	1.531 367.4	1.812 429.4	2.062 483.1	2.344 542.1	
26	26.000			.312 85.60	.500 136.17			.375 102.63			.500 136.17	<i>Factores Para Níquel y Otras Aleaciones</i>					
28	28.000			.312 92.26	.500 146.85	.625 182.73		.375 110.64				Titanio 0.582 Aleación 600 1.0742					
30	30.000	.250 79.43		.312 98.93	.500 157.53	.625 196.08		.375 118.65			.500 157.53	Acero al Carbono 0.993 Aleación C-276 1.129					
32	32.000			.312 105.59	.500 168.21	.625 209.43		.375 126.66	.688 230.08		.500 168.21	Aleación 2205 0.997 Aleación 400 1.1272					
34	34.000			.312 112.25	.500 178.89	.625 222.78		.375 134.67	.688 244.77			Aleación 800 1.0247 Níquel 200 1.1343					
36	36.000			.312 118.92		.625 236.13		.375 142.68	.750 262.35		.500 189.57	Aleación 825 1.0389 Níquel 201 1.1378					
												Aleación 625 1.068 Aleación 20 1.0220					
Para calcular el peso teórico use los factores de la lista y multiplique por el peso por pie (Números Rojos).																	